



Aristide nv
Nachtegalstraat 109
2550 KONTICH

Your notice of
14-02-2023

Your reference

Date
24-02-2023

Analysis Report 23.00842.11

Required tests :

California Technical Bulletin 117 (2013)

Sample id	Information given by the client	Date of receipt
T2303490	CABRO 01 CAMEL	14-02-2023

Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2303490 - CABRO 01 CAMEL

Section 1 : cover fabric test

Date of ending the test 24-02-2023
Standard used ASTM E1353-08a (2013)
Product standard California Technical Bulletin 117 (2013)

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

Filling T 30130 (Recticel) - non-fire retardant foam
Cover Sheeting Material Composition 100 % cotton - laundered weight (125 ± 28) g/m²

	1#	2#	3#
Open flaming	no	no	no
Smoulders more than 45 min.	no	no	no
Vertical char length > 45 mm	no	no	no

cigarette fails to smoulder its complete length

Test criteria

- no open flaming
- smouldering ≤ 45 minutes
- vertical char ≤ 45 mm

Requirements

- all specimens meet the test criteria → PASS
- two or more specimens fail the test criteria → FAIL
- one specimen fails the test criteria → 3 additional tests → PASS
- all specimens meet the test criteria

Conclusion Pass