

Lyon Road Industrial Estate : Kearsley : Bolton Lancashire : BL4 8NB Tel: +44 (0) 1204 792858 Email: enquiries@ltslab.co.uk

www.ltslab.co.uk



9630

TEST CERTIFICATE

CLIENT: Aristide NV Certificate Number: UK2201281-1

Nachtegaalstraat

BE-BE2550 Kontich Date Received: 16/09/2022

Belgium

Date Issued: 20/09/2022

-

Issue Number:

Changes made from previous issue (if applicable)

Contact: Pieter-Jen Debusschere

Tel: +32 3 458 05 94 **Email:** info@aristide.be

SAMPLE IDENTIFICATION

The information is this section is provided by the client and Lancashire Testing Services Ltd assumes no reponsibility or liability for its accuracy.

Sample Name / Reference Apollo

Additional Names: -

Batch Ref/Number: B5739010003

Order Number: -

Colour: 105

Fabric Composition: 80% PES, 16% MAC, 4% RAY

Customer: -

SPECIFICATION

BS EN 1021-1:2014 Part 1: Ignition source smouldering cigarette

TEST METHOD

Flammability: BS EN 1021-1:2014 Part 1: Ignition source smouldering cigarette

BS EN 1021-2:2014 Part 2: Ignition source match flame equivalent

Pre-treatment: BS EN 1021-1:2014 Annex D - Water soaking procedure

Conclusion

The sample tested complies with the flammability requirements of BS EN 1021-1:2014 Smouldering Cigarette Source taking into account uncertainty of measurement

The sample tested complies with the flammability requirements of BS EN 1021-2:2014 Butane Ignition Source taking into account uncertainty of measurement

Uncertainty of Measurement: ±1 second - timing measurements, ±1mm - dimensional measurements

Comments:



Lyon Road Industrial Estate : Kearsley : Bolton Lancashire: BL4 8NB Tel: +44 (0) 1204 792858 Email: enquiries@ltslab.co.uk www.ltslab.co.uk



9630

TEST CERTIFICATE

Test Results:-						
BS EN 1021-1:2014: Smo	ouldering Cig	garette Source				
Assessment of the ignit	ability of uph	olstered furniture				
"The following test results relate				onditions of test;	they are not	
intended as a means of assessir	<u> </u>		n use."			
Sample Code	UK2201281 -1					
Sample Name / Reference	Apollo	Apollo				
Client	Aristide NV	Aristide NV				
Date of test		20/09/2022				
Pre-Treatment	ent BS EN 1021-1:2014 Annex D - Water soaking procedure					
	Line Dried					
Filling Type	Carpenter/RX3	arpenter/RX36110 Combustion Modified Foam Density 34-36kg/m³ /105-115N				
Size of test rig	Small: Back - 4	150 x 300 ± 2mm + Seat - 450	x 150 ± 2mm	_		
Test Conditions	Period h	Temperature ⁰C	Relative humidity %	Air Flow m/s	Volume m ³	
Conditioning of test specimens	≥24	23±2	50±5	≤0.2	-	
Testing conditions	-	10-30	15-80	0.05	≥6	
Testing Source	Smouldering Cigarette Source					
Testing time limit	time limit 60 minutes after placement of smouldering cigarette.					
Test 1 Test 2 Test 3				st 3		
Time for cigarette to smoulder to completion (min:sec)		23.17	29.44	N/A		
3.1a Escalating combustion behaviour observed so that it was unsafe to continue the test and active extinction was necessary		NO	NO	N/A		
3.1b Smouldering which largely consumed the test assembly within the test period		NO	NO	N/A		
3.1c Smouldering to the extremities of the specimen, upper or lower margins, either side or to its full thickness, within the duration of the test		NO	NO	N/A		
3.1d Smouldering after one hour from the beginning of the test		NO	NO	N/A		
3.1e On final examination, evidence of active smouldering		NO	NO	N/A		
3.2 Occurrence of flames initiated by a smouldering source		NO	NO	N/A		
Test Result:		PASS	PASS	NOT T	ESTED	

RESULT:	SMOULDERING CIGARETTE SOURCE	PASS

Please note that copies of this original certificate are not valid

Issue Number: 1



Lyon Road Industrial Estate : Kearsley : Bolton Lancashire: BL4 8NB Tel: +44 (0) 1204 792858 Email: enquiries@ltslab.co.uk

www.ltslab.co.uk



9630

TEST CERTIFICATE

Test Results:-						
BS EN 1021-2:2014: Bu	utane Source 1	<u>[</u>				
Assessment of the ign	itability of uph	olstered furniture				
"The following test results relations intended as a means of assess				e particular co	onditions of test;	they are not
Sample Code		-1				
Sample Name / Reference	Apollo					
Client	Aristide NV					
Date of test	20/09/2022	****				
Pre-Treatment	BS EN 1021-1	:2014 Annex D - Water soakir	ng procedure			
	Line Dried					
Filling Type	Carpenter/RX3	86110 Combustion Modified Fo	oam Density 34	l-36kg/m³ /105	5-115N	
Size of test rig	Small: Back - 4	450 x 300 ± 2mm + Seat - 450	x 150 ± 2mm			
Test Conditions	-	Temperature ⁰C	Relative h	numidity %	Air Flow m/s	Volume m ³
Conditioning of test specimens	≥24	23±2	50:	±20	≤0.2	-
Testing conditions	-	10-30	15·	-80	0.05 ≥6	
Testing Source	Source Butane Flame Ignition Source 1					
Testing time limit	ne limit 2 minutes after removal of burner tube (120 seconds)					
		Test 1	Tes	st 2	Test 3	
Time for flames out (sec)		0	()	0	
3.1a/3.2a Escalating combustion behaviour observed so that it was unsafe to continue the test and active extinction was necessary		NO	N	0	NO	
3.1b Smouldering which largely consumed the test assembly within the test period		NO	N	0	NO	
3.1c Smouldering to the extremities of the specimen, upper or lower margins, either side or to its full thickness, within the duration of the test		NO	N	NO NO		0
3.1d Smouldering after one hour from the beginning of the test		NO	NO I		0	
3.1e On final examination, evidence of active smouldering		NO	NO		NO	
3.2b Smouldering which largely consumed the test assembly within the test period		ОИ	NO		NO	
3.2c Flame Front reached the extremities of the specimen, upper or lower margins, either side or to its full thickness, within the duration of the test		NO	NO		NO	
3.2d flaming continued for more than 120 seconds after removal of the burner tube		NO	NO NO		0	
Test Result:		PASS	PA	PASS PASS		SS
RESULT:	RESULT: BUTANE IGNITION SOURCE 1 PASS					

Issue Number: 1



Lyon Road Industrial Estate: Kearsley: Bolton
Please note that copies bankashijikal Buffiëlde are not valid
Tel: +44 (0) 1204 792858
Email: enquiries@ltslab.co.uk
www.ltslab.co.uk



9630

TEST CERTIFICATE

Certificate Number: UK2201281-1 Date of Issue: 20/09/2022

			PColling
Craig Allardice	Tony Alcock	John Marsh	Peter Collings
Laboratory Technician	Laboratory Technician	Laboratory Supervisor	Operations Manager

Decision Rule:

Lancashire Testing Services have measurement uncertainties for all test standards (available on request) and have applied these measurements to the test result.

The specific level of risk is < 2.5% as stated in ILAC-G8:09/2019. Unless otherwise indicated L.T.S will apply this rule to all measurements reported.

If the measurement result plus/minus the expanded uncertainty with a 95 % coverage probability overlaps the limit, it is not possible to state compliance or non-compliance. The measurement result and the expanded uncertainty with a 95 % coverage probability will then be reported. The report will include the actual value with the uncertainty range.

Lancashire Testing Services Ltd have conducted thorough analysis of the uncertainty of all measurements carried out in the application of the standard or standards detailed in this report. Where possible any associated uncertainty of measurements have been accounted for in the working instructions, so that they have no impact on the reporting of the final result. In instances were uncertainty of measurements can only be taken into account after the test has been conducted, these uncertainty values have been stated on this report. The stated uncertainty of measurement has also been taken into account in the final reporting of the overall result.

Information provided about a customer, from a source other than the customer, shall only be shared with the customer. The provider of the information shall remain confidential to the laboratory unless agreed by the source of the information.

Issue Number: 1

Please note that copies of this original certificate are not valid